

EtaProof-Spezifikationen

	Norm/Standard	Unit	EtaProof 145	EtaProof 170	EtaProof 200	EtaProof 240	EtaProof 270	EtaProof 300	EtaProof 220 RS	EtaProof 200 Bio	
FABRIC WIDTH MINIMUM		cm	150	150	150	150	150	100	150	150	
FABRIC WEIGHT	ISO 3801	g/m ² +/- 5%	145	170	200	240	270	300	220	200	
THREADS/CM		Kette/Warp	92	96	81	66	68	71	81	81	
		Schuss/Weft	41	35	30	26	26	26	30	30	
BREAKING STRENGTH	DIN EN ISO 13934-1	warp minimum	1000	1000	1100	1400	1200	1500	1200	1100	
		weft minimum	650	650	650	750	1000	1400	750	650	
TEAR STRENGTH	DIN EN ISO 13937-1	warp minimum	900	900	1200	1800	1800	2200	1350	1200	
		weft minimum	650	650	750	1200	1600	1600	800	750	
DIMENSIONAL STABILITY	ISO 6330	Mashine wash 30°C									
		warp maximum	%	+/-3.0	+/-3.0	+/-3.0	+/-3.0	+/-3.0	+/-3.0	+/-3.0	+/-3.0
		weft maximum	%	+/-3.0	+/-3.0	+/-3.0	+/-3.0	+/-3.0	+/-3.0	+/-3.0	+/-3.0
WATER REPELLENCY	DIN EN 29865	Bundesmann 30 min Test									
		Water repellency	Note/rating	4	4	4	4	4	4	4	4
		Water absorption	Maximum %	10	10	10	10	10	10	10	15
		Water penetration	Maximum ml	0	0	0	0	0	0	0	0
HYDROSTATIC HEAD	DIN EN 20811	mm of water column	750	750	750	750	750	900	600	600	
		max. No. of globules after 5 min	3	3	3	3	3	3	3	3	
WATER VAPOUR PERMEABILITY	ISO 11092	Ret m ² xPa/w	6	6	6	6	6	7	6	6	

Natural performance.....

